# EMERALD POWDER FREE, BEADED CUFF

MATERIAL : 100% Synthetic Nitrile Latex GLOVE WEIGHT (grm) : Small: 3.2 Medium: 3.5 Large: 3.8 Extra-Large: 4.1

Length (mm)



Walletz4u® Emerald Prime

#### REORDER CODE:-NBR PF USAW35 BB

- WZPNUS0S82064 (SIZE S)
- WZPNUS0M82026 (SIZE M)
- WZPNUSOL82033 (SIZE L)
- WZPNUSXL82057 (SIZE XL)

#### **FEATURES**

- Fingertip textured
- Powder free
- Not made with natural rubber latex
- Lab Chemical tested
- Chemo Drugs tested
- Ambidextrous
- Blue colour

#### PACKAGING

100 gloves per box 10 boxes per carton

#### **REGULATORY COMPLIANCE**

FDA 510(k), MDD 93/42/EEC, ASTM D6978-05

#### **STANDARDS**

ASTM D6319 ASTM D5151, ASTM D6124, EN455

#### MANUFACTURING ACCREDITATIONS

ISO 9001:2015 ISO 13485:2016

| ≥230             |   |
|------------------|---|
|                  |   |
| 0.07 ± 0.02      |   |
| 0.09 ± 0.02      |   |
| Before Aging     | After Aging   |
| ≥16              | ≥18   |
| ≥500             | ≥400  |
| Inspection Level | AQL   |
| G1               | 1.5   |
| S2               | 4.0   |
| S2               | 4.0   |
| S4               | 2.5   |
| S4               | 4.0   |
| N = 5            | ≥2mg/glove  |
|                  | 0.07 ±<br>0.09 ±<br>Before Aging<br>≥16<br>≥500<br>Inspection Level<br>G1<br>S2<br>S2<br>S2<br>S4<br>S4<br>S4 |

| Chemotherapy Drugs and Concentration<br>(Tested for Resistance to Permeation by Chemotherapy<br>Drugs as per ASTM D6978-05) | Minimum Breakthrough<br>Detection Time (minutes) |
|---|--|
| Carmustine (BCNU), 3.3mg/ml (3,300 ppm)   | Not recommended                                  |
| Cisplatin, 1.0mg/ml (1,000 ppm)   | >240 minutes                                     |
| Cyclophosphamide (Cytoxan), 20.0mg/ml (20,000 ppm)  | >240 minutes                                     |
| Dacarbazine (DTIC), 10.0mg/ml (10,000 ppm)  | >240 minutes                                     |
| Doxorubicin Hydrochloride, 2.0mg/ml (2,000 ppm)   | >240 minutes                                     |
| Etoposide (Toposar), 20.00mg/ml (20,000 ppm)  | >240 minutes                                     |
| Fluorouracil, 50.0mg/ml (50,000 ppm)  | >240 minutes                                     |
| Methotrexate, 25.0mg/ml (25,000 ppm)  | >240 minutes                                     |
| Mitomycin C, 0.5mg/ml (500 ppm)   | >240 minutes                                     |
| Paclitaxel (Taxol), 6.0mg/ml (6,000 ppm)  | >240 minutes                                     |
| Thiotepa, 10.0mg/ml (10,000 ppm)  | Not recommended                                  |
| Vincristine Sulfate, 1.0mg/ml (1,000 ppm)   | >240 minutes                                     |

WARNING: Gloves used for protection against chemotherapy drug exposure should be selected specifically for the type of chemicals being used. Due to the variety and concentration of chemotherapy drugs used in treatments, the resistance table shown does neither warrant nor imply the safe use of the gloves against chemotherapy drugs resistance in every case. The safe use of gloves in chemotherapy treatment is solely the decision of clinicians authorised to make such decision.

## 800-603-9855 info@healthtechintlinc.com

### **08** PRODUCT CATALOGUE